

OB1 SEALANT REMOVER

Benefits

- Removes silicone and sealants quickly
- Highly effective
- Low odour

Recommended Areas of Use

- Uncoated aluminium and its alloys, copper and its alloys, iron and steels, glass, ceramics and epoxy composites

Product Description

OB1 Sealant Remover is a low odour formulation that does not contain halogenated solvents, heavy metals, cyanide or water. It will also help to remove silicone overspray on masonry and silicone oil stains on porous materials.

Directions of use

To remove silicone sealants or gaskets, carefully cut away as much of the silicone as possible. Apply OB1 Sealant Remover to completely cover the remaining silicone that needs to be removed. The depth of cover should be at least twice as deep as the depth of silicone to be removed. Leave to sit for 1-12 hrs (time varies depending on the characteristics of the substrate). Rinse thoroughly with water and repeat process if necessary.

Storage

Store locked up in dry conditions between 0°C and +30°C in original, unopened container and protect from frost. Some darkening may occur during storage.

Shelf Life

12 months from date of manufacture.

Limitations

Contamination with water or oxygenated solvents must be avoided as this will render OB1 Sealant Remover inactive and may cause it to affect other materials. OB1 Sealant Remover will attack nylon (polyamide) and may have a softening effect on some non-silicone sealants. On granite/quartz/marble surfaces it is advisable to test a small hidden area before use. It is the user's responsibility to determine suitability.



Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.